# Available online atwww.scholarsresearchlibrary.com



Scholars Research Library

Archives of Applied Science Research, 2015, 7 (5):16-21 (http://scholarsresearchlibrary.com/archive.html)



# Synthesis, characterization and biological evolution of polymeric ligand

# S. D. Patel<sup>1</sup>\* and V. M. Mistry<sup>2</sup>

<sup>1</sup>Department of Chemistry, J & J College of Science, Nadiad(India) <sup>2</sup>Pacific University, Udaipur

## ABSTRACT

Diazotization reaction of resorciacetophenonel-Formaldehyde polymer with 4-methyl benzenediazonium salt was synthesized novel ligand based on phenylazo of resorciacetophenonel-Formaldehyde polymer. Co-ordination polymers of this ligand were prepared with Cu(II),Ni(II),Co(II),Mn(II) and Zn(II) metal ions. All of these coordination polymers and the ligand were characterized by elemental analyses by IR, NMR, number-average

molecular weights ( Mn ), magnetic susceptibilities and by thermogravimetry. The biological activity of all the samples has also been monitored against plant pathogens.

Keywords: Bis(bidentate) ligand, Coordination polymers, Number average molecular weight(Mn), IR, Thermogravimetric analysis(TGA), magnetic moment and Antifungal activities.

#### INTRODUCTION

Phenolic resins are commodity materials for wide applications [1,2]. Metal Containing polymers have important applications in medical sciences [3-5]. The presence of metals in polymeric materials leads to new physical properties and potential applications. Several different possible types of metal-containing polymer structures exist depending on where the metal atoms are incorporated and the nature of the linkages between them. A major subdivision of linear polymers involves a consideration of the location of the metallocenters. Coordination polymers are light in weight and posses high thermal stability. Polymeric metal complexes have a variety of geometries that are not observed in organic polymers, some combine the properties of anisotropy with photo responsive behaviour that give rise to applications in areas such as optical storage, optical switching, diffractive optical elements, non-linear optical devices, liquid crystal displays (LCD's) etc.[6-8].Metal complex dyes comprise an important class of chromophores. These dyes have been deeply investigated since antiquity [9] and have been widely used in many practical applications; textile dyeing, colouring polyamide fibers, are typical traditional uses [10, 11]. Hence the present article describes the synthesis and characterization of a novel ligand phenyl azo of resorciacetophenonel-Formaldehyde polymer and its coordination polymers with Cu(II),Co(II),Ni(II),Mn(II), and Zn(II) metal ions. The synthetic route is shown in scheme 1.



Metal complex of TARF polymer Where, M = Cu(II), Ni(II), Co(II), Mn(II), and Zn(II)

Scheme 1

#### MATERIALS AND METHODS

## Materials

All chemicals used were of analytical pure grade.

# Synthesis of azo coupling of 4-methyl benzene diazonium salts to resorciacetophenonel-Formaldehyde polymer (TARF)

The resorciacetophenonel-Formaldehyde polymer was prepared by method reported in literature [12].

Diazonium salt of 4-methyl benzene solution (0.1mole) was slowly added to an alkaline solution of resorciacetophenonel-Formaldehyde polymer (RF) (0.1mole) at pH 8.5-9.0 and below 0-5°C. The resultant solution was stirred for 3hr.The dye was precipitated by lowering the pH to 6.0.The precipitated dye (TARF) was filtered off, wash with water and air-dried. The yield of TARF was 64% and m.p.236-238°C (uncorrected). The predicted structure and formation of polymeric ligand is shown in Scheme-1.

<b>Analysis of TARF:</b> $C_{33}H_{30}N_2O_9$ (598)						
	C%	Н%	N%			
Calculated:	66.22	5.02	4.68			
Found:	66.2	4.9	4.6			

IR Spectral Features (cm<sup>-1</sup>): 3030, 1520, 1640 (Aromatic), 1720 (CO), 3450-3160(OH), 2890, 2940(CH<sub>2</sub>,CH<sub>3</sub>).

Scholars Research Library

#### **Preparation of Coordination Polymers**

All coordination polymers were synthesized by using metal acetate by the method described below.

A warm clear solution of TARF (0.01 mol) in 20% aqueous formic acid (200 ml) was added to a solution of metal acetate (0.01 mol) in 50% aqueous formic acid (50 ml) with constant stirring. After complete addition of the metal salt solution, the pH of the reaction mixture was adjusted to about 5 with dilute ammonia solution. The Coordination polymers thus separated out in the form of a suspension was digested on a water bath for 1 h and eventually filtered, washed with hot water followed by acetone and dimethyl formamide (DMF) and then dried in air at room temperature. The yields of all coordination polymers were almost quantitative.

Ligand/ Co-ordination polymers	Emperical Formula	Yield (%)	Elemental analysis Calc. / (Found)			µeffª		-	
	(Formula weight)		С	Н	Ν	Μ	( <b>B.M</b> )	(Mn) <u>+</u> 60	Dp
TARF	$C_{33}H_{30}N_2O_9$	64	66.22	5.02	4.68	_	-	-	-
	(598)		(66.2)	(4.9)	(4.6)		_		
[CuTARF(H <sub>2</sub> O) <sub>2</sub> ]n	Cu.C <sub>66</sub> H <sub>58</sub> N <sub>4</sub> O <sub>18</sub> .2H <sub>2</sub> 0	74	61.23	4.79	4.33	4.91	1.8	6534	5
	(1293.54)		(61.2)	(4.7)	(4.3)	(4.8)			
[CoTARF(H <sub>2</sub> O) <sub>2</sub> ]n	Co. C <sub>66</sub> H <sub>58</sub> N <sub>4</sub> O <sub>18</sub> .2H <sub>2</sub> 0	71	61.45	4.81	4.34	4.57	3.6	7788	6
	(1288.94)		(61.4)	(4.8)	(4.3)	(4.5)			
[NiTARF (H <sub>2</sub> O) <sub>2</sub> ]n	Ni. C <sub>66</sub> H <sub>58</sub> N <sub>4</sub> O <sub>18</sub> .2H <sub>2</sub> 0	69	61.46	4.81	4.35	4.56	3.2	7790	6
	(1288.71)		(61.4)	(4.7)	(4.3)	(4.5)			0
[MnTARF(H2O)2]n	Mn. C66H58N4O18.2H20	75	61.64	4.83	4.36	4.28	5.4	6485	5
	(1284.94)		(61.6)	(4.8)	(4.3)	(4.2)			3
[ZnTARF(H <sub>2</sub> O) <sub>2</sub> ]n	Zn. C <sub>66</sub> H <sub>58</sub> N <sub>4</sub> O <sub>18</sub> .2H <sub>2</sub> O	72	61.14	4.79	4.32	5.05	D	7823	6
	(1295.98)		(61.1)	(4.7)	(4.3)	(5.0)			0

Table 1 Analytical data of coordination polymers of TARF (H<sub>2</sub>L)

<sup>a</sup>Magnetic moment; D is diamagnetic.

#### **MESUREMENTS**

Elemental analyses of TARF and its coordination polymers were carried out on a Thermofingan flash 1101EA (Italy). The metal content of the coordination polymers were performed by decomposing a weighed amount of coordination polymer followed by complexometric titration with EDTA (disodium ethylene diamine tetra acetate) [13]. Infrared (IR) spectra of all the samples were scanned on a Nicolet-760 FTIR spectrophotometer in KBr and <sup>1</sup>H NMR spectrum of TARF was recorded in DMSO with TMS as internal standard on Brucker spectrophotometer at

400 MHz. The number average molecular weight (Mn) of all the coordination polymers were determined by method reported in earlier communications [14].

Magnetic susceptibility measurements of all the coordination polymers were carried out at room temperature by the Gouy method. Mercury tetrathio cynato cobaltate (II)  $Hg[Co(NCS)_4]$ , was used as a calibrant Molar susceptibilities were corrected for diamagnetism of component atoms using Pascal's Constant [15]. The solid diffuse reflectance spectra of all the coordination polymers samples were recorded on a Beckman DK-2A spectrophotometer with a solid reflectance attachment. MgO was employed as the reference compound.

Ligand/	% Weight loss at different temperature( <sup>0</sup> C)						
<b>Co-ordination polymers</b>	100	200	300	400	500	600	700
TARF	-	8.89	9.31	23.43	28.07	31.45	34.11
[Cu TARF(H <sub>2</sub> O) <sub>2</sub> ]n	1.14	8.67	11.84	26.46	30.51	33.43	37.18
[Co TARF(H <sub>2</sub> O) <sub>2</sub> ]n	1.75	12.63	24.48	38.34	52.12	64.54	67.25
[NiTARF (H <sub>2</sub> O) <sub>2</sub> ]n	2.67	15.42	18.53	36.61	52.63	65.47	68.04
[MnTARF(H2O)2]n	2.36	9.97	13.67	34.42	53.23	66.08	68.53
[Zn TARF(H <sub>2</sub> O) <sub>2</sub> ]n	6.67	15.26	31.32	36.59	55.35	66.13	69.55

Table 2 Thermogravimetric analysis of TARF ligand and its co-ordination polymers

Thermogravimetric analysis of coordination polymers were carried on DuPont 950 TGA analyzer in air at a heating rate of 20C/min.

#### Antifungal activities

The fungicidal activity of all the compounds was studied at 1000 ppm concentration in vitro. Plant pathogenic organisms used were *penicillium expansum*, *Botrydepladia thiobromine and Nigrospora Sp.*. The antifungal activity of ligand and its coordination polymers (1a-e) was measured on each of these plant pathogenic strains on a potato dextrose agar (PDA) medium. Such a PDA medium contained potato 200gm,dextrose 20gm,agar20gm and water one liter. Five days old cultures were employed. The compounds to be tested were suspended (1000ppm) in a PDA medium and autoclaved at 120° C for 15 min. at 15atm.pressure. These medium were poured into sterile Petri plates and the organisms were inoculated after cooling the Petri plates. The percentage inhibition for fungi was calculated after five days using the formula given below:

## Percentage of inhibition = 100(X-Y) / X

Where, X =Area of colony in control plate Y =Area of colony in test plate

Table 3 Antifung	gal Activity of	co-ordination	polymers.
------------------	-----------------	---------------	-----------

Zone of Inhibition at 1000 ppm (%)							
Compounds	Penicillium Expansum	Botrydepladia Thiobromine	Nigrospora Sp.				
[Cu TARF(H <sub>2</sub> O) <sub>2</sub> ]n	69	60	70				
[Co TARF(H <sub>2</sub> O) <sub>2</sub> ]n	60	68	62				
[Ni TARF (H <sub>2</sub> O) <sub>2</sub> ]n	68	66	71				
[MnTARF(H <sub>2</sub> O) <sub>2</sub> ]n	69	69	64				
[Zn TARF(H <sub>2</sub> O) <sub>2</sub> ]n	55	59	67				

#### **RESULTS AND DISCUSSION**

The synthesis of the bidentate ligand phenylazo of resorciacetophenonel-Formaldehyde polymer has been not reported previously. It was prepared by diazotization reaction of resorciacetophenonel-Formaldehyde polymer with 4-methylbenzenediazoniumsalt. The ligand TARF was isolated in form of a light brown powder. It is soluble in organic solvents such as dioxane, DMSO and DMF. The results of elemental analyses of the TARF ligand (Table-1) are agreed with those predicted on the basis of formula.

The IR spectrum of TARF shows a broad band extending from 3400-3100 cm<sup>-1</sup> with maximum at 3330 cm<sup>-1</sup> attributed to –OH group. The weak bands at 2932cm<sup>-1</sup> and 2850cm<sup>-1</sup> are attributed to asymmetric and symmetric stretching vibrations of methylene groups. The band at 1720 cm<sup>-1</sup> due to CO group.

The coordination polymers derived from TARF and metal ions Cu(II), Co(II), Ni(II), Mn(II) and Zn(II) vary in color from light red to brown, These polymers do not melt upto  $360^{\circ}$ C. On the basis of the proposed structure shown in Scheme1, the molecular formula of the TARF ligand is  $C_{33}H_{30}N_2O_9$ , which, upon chelation coordinates with one central metal atom at four coordination sites and two water molecules. Therefore, the general molecular formula of the resulting coordination polymer is given by [M(TARF)<sub>2</sub>.2H<sub>2</sub>O] as shown in scheme 1. This has been confirmed by the results of elemental analyses of all of the five coordination polymers and their parent ligand. The data of elemental analyses reported in Table 1 are in agreement with the calculated values of C,H, and N based on the above-mentioned molecular formula of the parent ligand as well as coordination polymers. Examination of data of the metal content in each polymer (Table I) revealed a 1:2 metal:ligand (M/L) stoichiometry in all of the coordination polymers.

One of the significant differences to be expected between the IR spectrum of the parent ligand and that of its metal coordination polymers is the presence of much broader bands in the region of 3000-3600cm<sup>-1</sup> for the coordination polymers, as the oxygen of the O-H group of the ligand forms a coordination bond with the metal ions. This is explained by the fact that water molecule could have strongly coordinated to the polymer samples during its formation. Another noticeable difference is that the band at 1600 cm<sup>-1</sup> in IR spectrum of TARF due to the C=N stretching is shifted toward lower frequency. The band at 1420cm<sup>-1</sup> in the IR spectrum of TARF assigned to inplane –OH deformation [16] is shifted toward higher frequency in the spectra of the coordination polymers indicating formation of metal-oxygen bond. This further confirmed by a weak band at 1110 cm<sup>-1</sup> corresponding to

Scholars Research Library

C-O-M band [16]. All of these features suggest that the structure of the coordination polymers is shown in scheme 1.

The value of the degree of polymerization of all the coordination polymers listed in Table 1 suggest that the average Dp for all the polymers in a range of 5 to 6.

Magnetic moments ( $\mu_{eff}$ ) of coordination polymers are given in Table 1. Examination of these data reveals that all coordination polymers except Zn (II) metal ion polymer are paramagnetic while that of Zn(II) metal ion polymer is diamagnetic.

The diffuse electronic spectrum of the [CuTARF(H<sub>2</sub>O)<sub>2</sub>] coordination polymers shows two broad bands around 15,974 cm<sup>-1</sup> and 22,792 cm<sup>-1</sup> due to the  $2_{T2g} \rightarrow 2_{Eg}$  transition while the second may be due to charge transfer, respectively, This suggest a distorted octahedral structure for the [CuTARF(H<sub>2</sub>O)<sub>2</sub>] polymer. The higher value of µeff of the [CuTARF(H<sub>2</sub>O)<sub>2</sub>] polymer support this view [17,18]. The [NiTARF(H<sub>2</sub>O)<sub>2</sub>] coordination polymer gave two absorption bands at 15,604 cm<sup>-1</sup> and 22,991 cm<sup>-1</sup> due to  $3_{A2g} \rightarrow 3_{T1g}$  (F) and  $3_{A2g} \rightarrow 3_{T1g}$  (P) respectively. The [CoL(H<sub>2</sub>O)<sub>2</sub>] polymer shows two absorption bands, at 19,619 and 22,928 cm<sup>-1</sup> corresponding to  $4_{T1g}$  (F)  $\rightarrow 4_{T2g}$  and  $4_{T1g}$ (F)  $\rightarrow 4_{T2g}$ (F) transitions, respectively[14]. Thus, the absorption bands of the diffuse reflectance spectra and the values of the magnetic moments(µ<sub>eff</sub>) indicate an octahedral configuration for the [Ni TARF (H<sub>2</sub>L)<sub>2</sub>] and [CoTARF(H<sub>2</sub>O)<sub>2</sub>] polymers[15,19]. The spectrum of [MnTARF(H<sub>2</sub>O)<sub>2</sub>] show weak bands at 16,481, 17,696 and 23,156 cm<sup>-1</sup> assigned to the transitions  $6_{A1g} \rightarrow 4_{T1g}$ (4G), $6_{A1g} \rightarrow _{4T2g}$ (4G) and  $6_{A1g} \rightarrow 4_{A1g}$ , $4_{Eg}$  respectively, suggesting an octahedral structure for the [MnPARF(H<sub>2</sub>O)<sub>2</sub>] polymer[19]. As the spectrum of the [ZnPARF(H<sub>2</sub>O)<sub>2</sub>] polymer is not well resolved, it is not interpreted, but its µ<sub>eff</sub> value shows that it is diamagnetic as expected.

The TGA data for the polymers are presented in Table 2. The weight loss of the polymer samples at different temperature indicates that the degradation of the polymers is noticeable beyond 300°C. The rate of degradation becomes a maximum at a temperature lying between 400°C and 500°C.This may be due to accelerating by metal oxide which forms in situ. Each polymer lost about 50% of its weight when heated up to 700°C. Inspection of the thermograms of all coordinated polymer samples revealed that all samples suffered appreciable weight loss in the range 150 to 280°C. This may be due to the presence of coordinated water molecule.

On the basis of the relative decomposition (% wt.loss) and the nature of thermogram, the co-ordination polymers may be arranged in order in decreasing stability as:

Mn>Zn>Co>Ni>Cu

The antimicrobial activity of TARF and its coordination polymers are presented in Tables 3. The data suggest that all the samples are toxic to fungus. The data also suggest that the % age of fungus is inhibited in the range of 55 to 71% depending upon the biospecies and coordination polymers.

## CONCLUSION

The present paper describes the novel bis-ligand having phenylazo of resorciacetophenonel-Formaldehyde polymer moieties. The Bis-ligand afforded the coordination polymers with metal ions. The polymers have moderate thermal stability. All the polymers have good microbicidal activity.

#### REFERENCES

[1] A.K. Sen, S.Roy and V.A.Juvekar, *International Scholarly Research Network*, **2012**, Article ID 514509.

[2] A.K.D Metra and A.Karchadhanvi, IInd. J. Chem., 2000, 39B,311.

[3] S. Roy, I.T.Y.Ohulchanskyy, H.E.Pudavar, E.J.Bergey, A.R.Oseroff, J.Morgan, T.J. Dougherry and P.N. Prasad, *Journal of American Chemical Society*, **2003**, 125(26), 7860-7865.

[4] F.Yang, C.Y. Xu, M. Kotaki, S.Wang and R.Ramakrishnal, J. of BiomaterialScience, 2004, 15(12),1483-1497.

[5] B.M. Ibrahim and S.M. Magani, African Scientist, 2010, 11(4), 51.

[6] I. Manners, Comprehensive Organometallic ChemistryIII, Elsevier, 2007, 1-13, 296-320.

[7] I.Kaya, H.O.Demir and A.R.Vilayetog lu, J. of Synthetic Metals, 2002, 126(1), 183-191.

Scholars Research Library

[8] N.Davidenko, A.N. Ishchenko and N.G.Kuvshinskij, Photonics of molecular Semiconductor Composites on the basis of organic Dyes. Kiev: Naukovadumka, **2005**, 201.

[9]M. Bankova, N. Manolova, N. Markova, T. Radoucheva, K.Dilova and I. Rashkov, *Eur. Polym. J.*, **1999**, 34 (2), 247.

[10. D W Rangnekar, V R Kanetkar, J V Malanker, G S Shankarling, *Indian J Fiber Text Res*, **1999**, 24, 142–4.

[11] N. Sekar, *Colourage*, **1999**,46,63–5.

[12] J. H. Burckhalter, and R. I. Leib, J. Org. Chem., **1961**, 26, 4078.

[13] A.I.Vogel, A Text book of Quantitative Inorganic Analysis, 3<sup>rd</sup>ed., (Longman, London), **1961**, 433.

[14] T. B. Shah, H. S. Patel, R. B. Dixit, and B. C. Dixit, Int. J. of Polym. Anal. and Charact., 2003,8,369.

- [15] J. Lewis and R.S. Wilkins, Modern Co-ordination Chemistry. Interscience, NY, 1960, 290.
- [16] R.G.Charles, H. F. Freiser, R. Priedel, L. E. Hilliand, R. D. Johnston, Spectrochem. Acta., 1956,8,1.
- [17] D.C.Patel and P. K. Bhattacharya, J. Indian Chem. Soc., 1972, 49, 1041.
- [18] D. Oza, K. N. Kaul and R. K. Mehta, Indian J. Chem., 1996, 7, 927.

[19] R. Papplardo, J. Chem. Phys., 1960,33,613.